



Top Roof G

Product Description

A single component elastomeric acrylic resin-based flexible acrylic waterproofing coating. The product consists of special mineral filler and polymer components, and has strong adherence ability. It gives an extremely durable insulation coating with excellent water and UV resistance. It is designed for walkable concrete roofs, under ceramic applications, terraces and foundations, walking paths, asphalt pavements, sports such as tennis courts. It can be used under ceramics and marble.

Uses areas:

- Concrete terrace and roof waterproofing.
- In wet area insulation.
- Concrete roads, parks and gardens.
- Chimney and parapet edges on roofs.
- On all horizontal and vertical surfaces.

Properties

- Waterproof
- Long lasting.
- Ultra-flexible (high crack bridging capability)
- Easy application.
- It can be colored
- Excellent adhesion.(Excellent bonding to most substrates)
- Odorless.
- Non-toxic, water-based, low VOC
- Excellent breath-ability
- Very low maintenance/repair costs
- Environmentally friendly

TECHNICAL PROPERTIES

<i>Appearance/Color</i>	White / Gray / Red Oxide/ Blue
<i>Density:</i>	1.45 kg/liter
<i>Volume solids %:</i>	58 %
<i>Theoretical spreading rate:</i>	1.90 m ² /ltr (300 micron DFT) – 1.3 m ² /kg
<i>Consumption:</i>	770-800 g /m ² for 300 micron thickness
<i>Recommended DFT:</i>	300 – 400 micron for Horizon surfaces.
<i>(Dry Film thickness)</i>	300 micron for Vertical Surfaces
<i>Surface dry:</i>	10 - 15 approx. min (s) 23°C/73.4°F 50% R.H.
<i>Light foot traffic</i>	5 -6 hours (23°C and 50% R.H.)
<i>Full dry:</i>	24 hours (23°C and 50 % R.H.)
<i>Application temperature:</i>	+10 °C/50° F and +35 °C/ 95°F

Application Details

<i>Application method:</i>	Brush / Roll / Airless Spray
<i>Thinner:</i>	Fresh water
<i>Thinner Amount:</i>	Brush (Do not Thin) – Roller (10 %) - airless Spray (5%)



Surface Preparation:

- Surface must be dry, clean and free of all contamination such as dirt, oil, grease, and coatings etc. which hinder adhesion.
- Surface must be firm and have enough strength. If in doubt, apply a test area before beginning.
- Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed.
- All dust, loose and friable particles should be removed from the surface before application with brush and/or vacuum cleaner.
- Grinding by diamond disk should take over the place and all the dust must be removed by vacuum machine.
- All the cracks must be repaired by Flexible Material.

PRECEDING COAT:

Concentrated Sealer

Important Remarks:

- Surfaces must have enough structural strength.
- Concrete should have minimum of 25 N/mm² compression resistance and minimum 1, 5 N/mm² tensile strength.
- Applications below 10°C should be avoided.
- The surface should be protected from moisture and rain for 24 hours after application.
- All application tools and equipment should be cleaned with water immediately after the use. Cured material can only be removed mechanically.
- Use only where application and drying can proceed at temperatures above: 10°C/50°F. The temperature of paint itself should be 15°C/59°F or above.

Shelf life & Storage:

12 months from date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +30°C.

Safety:

For information and precautions on the safe handling, transportation storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notice:

The information presented herein is given in good faith but without warranty. It's based on our experience, indicates our laboratory work results and does not necessarily indicate final product performance. We cannot be held liable for the results obtained with our products and for any loss or accident that may result from its use. Our suggestions don't release you from the obligation to check their validity and to test our products for both your process and end use application. All our products are sold in accordance with our General Conditions of Sale. We don't make any warranty, express or implied, including but not limited to the merchant ability and fitness for a particular purpose.